






SPECIFICATIONS		
Nominal Voltage		12V
Rated Capacity (20 hour rate)		7.0Ah
Dimensions	Total Height (with terminals)	3.94inches (100mm)
	Height	3.70inches (94mm)
	Length	5.94inches (151mm)
	Width	2.56inches (65mm)
Weight		Approx. 4.4pound (2.0kg)

CHARACTERISTICS		
Capacity 77°F (25°C)	20 hour rate (0.35A)	7.0Ah
	10 hour rate (0.65A)	6.5Ah
	5 hour rate (1.12A)	5.6Ah
	1 hour rate (4.20A)	4.2Ah
	15 minute Rate (12.3A)	3.1Ah
Internal Resistance	Full charged Battery 77°F (25°C)	26mΩ
Capacity affected by Temperature (20 hour rate)	104°F (40°C)	102%
	77°F (25°C)	100%
	32°F (0°C)	85%
	5°F (-15°C)	65%
Self-Discharge 77°F (20°C)	Capacity after 3 month storage	91%
	Capacity after 6 month storage	81%
	Capacity after 12 month storage	60%
Max. Discharge Current 77°F (25°C)	105A(5S)	
Terminal	F1\F2	
Charge (Constant Voltage)	Cycle	Initial Charging Current less than 2.1A Voltage 14.4~14.7V/77°F (25°C)
	Float	Voltage 13.5~13.8V/77°F (25°C)

Discharge Curves 77°F (25°C)



Relationship between charge voltage and temperature




CONSTANT CURRENT DISCHARGE (amperes @25°C)											
F.V/Time	5Min	10Min	15Min	30Min	60Min	2H	3H	4H	5H	10H	20H
9.60	26.67	16.94	13.58	7.56	4.62	2.61	1.80	1.44	1.22	0.67	0.35
9.90	26.04	16.45	13.09	7.35	4.50	2.52	1.78	1.43	1.21	0.66	0.35
10.20	24.85	15.75	12.67	7.21	4.38	2.49	1.76	1.41	1.20	0.65	0.35
10.50	23.80	15.12	12.18	7.14	4.27	2.45	1.75	1.40	1.19	0.65	0.35
10.80	22.40	14.98	11.55	6.93	4.13	2.38	1.72	1.37	1.18	0.64	0.34


CONSTANT POWER DISCHARGE (watts per cell @25°C)											
F.V/Time	5Min	10Min	15Min	30Min	60Min	2H	3H	4H	5H	10H	20H
9.60	297.10	190.41	154.27	86.18	53.31	30.52	21.39	17.17	14.52	7.95	4.26
9.90	290.35	185.06	148.83	84.16	52.03	29.48	21.18	17.04	14.49	7.89	4.24
10.20	277.33	177.35	144.18	82.63	50.62	29.12	20.95	16.88	14.39	7.83	4.23
10.50	265.85	170.55	138.73	81.90	49.45	28.76	20.88	16.73	14.23	7.83	4.21
10.80	250.43	169.27	131.69	79.56	47.91	27.97	20.58	16.33	14.08	7.66	4.14

The operating environment temperature above 40°C should be avoided, after long term storage, the battery actual capacity would be less than the rated capacity. Full capacity will be obtained through several charge/discharge cycles. To get the longest lif the battery should be fully charged before storage.


Cycle service life in relation to depth of discharge




Constant voltage charge characteristic




Self-Discharge characteristic



Relationship of OCV and Residual Capacity % (25°C)



Temperature effects on capacity



Temperature effects on float life

